

OKOUME THROUGHOUT PLYWOOD

100% OKOUME

INTERIOR

EXTERIOR WBP

EXTERIOR CTBX/KOMO FSC

An acknowledged specie
for demanding jobs



Managing forests,
Enriching wood



Rougier

Gérer la forêt, faire vivre le bois

100% OKOUME

INTERIOR

EXTERIOR WBP

EXTERIOR CTBX/KOMO FSC

ROUGIER has selected this plywood for its versatility of use and its complementarity to traditional plywood. It is an economical product combining price and performance, respecting the technical, environmental and sanitary standards in force. Today, all the wood used to make plywood panels comes from forest concessions under sustainable management (CFAD), or from FSC-certified forest concessions, in other words they are conform to high environmental and social requirements.



INTERIOR

- Interior fitting
- Carpentry
- Decoration
- Stand

EXTERIOR

- Exterior fitting and shop fittings
- House cladding, roofing
- Walls, flooring, structural jobs
- Joinery, shuttering, body work

COMPOSITION AND ORIGIN

Support and Okoume faces.

Three types of bonding :

- Interior (UFU)
- Exterior WBP (Phenolic + Melamine)
- Exterior CTBX/KOMO FSC (Melamine)

Faces quality: II/III

Density (kg/m²) : 480 +/- 10%

COMPLIES WITH REQUIREMENTS AND RECOMMENDATIONS OF EUROPEAN STANDARDS

EN 635-1 et 2: Surface appearance

EN 315: Tolerances for dimensions

INTERIOR (UFU)

EN 636-1: use for dry conditions

EXTERIOR

EN 314-2, class 3: Bonding for exterior use

Notification CE 0380 CPD 0493

EN 717-1: no formaldehyde release (E0)

Compliance with EN 13986 : use of wood based panels in construction

CE marking: certificate of compliance 2+ according to EN 636-3

STANDARD FORMATS IN CM

Formats: 250 x 122 - 310 x 153

* other formats (please contact us)

Thickness: 3 - 4 - 5 - 8 - 10 - 12 - 15 - 18 - 22 - 25 - 30 - 35 - 40 mm

Specie: Okoume - Origin: Gabon